



CRACK TROWEL

LATEX CONCRETE REPAIR

Use from Featheredge to 1/4" per application
Yields 40 sq. ft. @ 1/8" for Trowel Applications
Has Up To 1 Hour Working Time

DANGER

Causes serious eye damage. Causes skin irritation.
May cause respiratory irritation. Causes damage to organs
(Lung) through prolonged or repeated exposure (inhalation).

KEEP OUT OF REACH OF CHILDREN

NET CONTENTS: 52 POUNDS

DO NOT ALLOW TO FREEZE



Use from Featheredge to 1/4" per application.

APPLY TO CLEAN SOUND SUBSTRATES. REMOVE ANY DUST, PAINT, CURING COMPOUNDS AND ANY FOREIGN MATTER FROM SURFACE PRIOR TO USE.

AFTER APPLICATION WAIT 6 TO 8 HOURS (depending on thickness and conditions) **PRIOR TO LIGHT TRAFFIC.**

MIX WITH LATEX LIQUID ONLY. 1 GALLON INCLUDED.

For Patch or Trowel Applications:

Approximately 1 gallon of Latex Liquid is required to mix 40 lb. of product.

Always add and mix product into liquid. Hold back 1 part latex liquid and adjust for consistency desired. Thorough mixing is required. Mix for 2-3 minutes until an even consistency is obtained. Apply material above 40° F. Rub or scratch mixed material onto surface just prior to application. Coverage will depend on thickness and substrate conditions.

FOR BEST RESULTS / LIMITATIONS:

Apply to clean, sound and stable substrates. Do not re-temper already mixed product. Check moisture content (mat test) prior to applying waterproof topping. Product is to be stored in a dry, cool place.

INGREDIENTS/CAS#:

Portland cement (65997-15-1);
Crystalline silica (14808-60-7);

NFPA® RATINGS:

Health: 3; Flammability: 0; Reactivity: 0



WARNING: This product can expose you to Crystalline Silica, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.



Please Recycle.

1857.061815