

ROCK & ROLL

Latex Concrete Repair

Form: Powder

Color: Gray to gray-brown

Odor: None

pH: N/A

Solubility (in water): Slight
(in mineral spirits): Insoluble

VOC Content (% by weight): None

Flash Point (ASTM D-7821): None

Specific Gravity: 2.6 - 3.2 g/cm³

Density: 21.7 - 26.7 lbs/gal

Storage Stability (at 70°F): Stable

<u>Ingredients</u>	<u>C.A.S. #</u>
Silica Sand, Crystalline.....	14808-60-7
Portland Cement.....	65997-15-1
Amorphous Silica.....	7631-86-9
Calcium Sulfate.....	10101-41-4 or 13397-24-5

Ideal for use on...

- Concrete Highways
- Roads
- Bridge Decks
- Loading Docks
- Brick Walls
- Concrete Parking Lots

Usage Amounts

<u>Bag Size</u>	<u>Latex Addition</u>	<u>Yield</u>
52 lbs	1 gallon	40 ft ² @ 1/8"

DIRECTIONS: Prepare holes according to label directions. Always add and mix product into liquid. Hold back 1 part latex liquid and adjust for consistency desired. Thorough mixing is required. Mix for 2 – 3 minutes until an even consistency is obtained. Apply material above 40°F. Rub or scratch mixed material onto surface just prior to application. Coverage will depend on thickness and substrate conditions. For best results / limitations: apply to clean, sound and stable substrates. Do not re-temper already mixed product. Check moisture content (mat test) prior to applying waterproof topping. Product is to be stored in a dry, cool place.

HMIS				NFPA	
		Severe	4	Extreme	
Health	2	Serious	3	High	Health..... 2
Flammability.....	0	Moderate	2	Moderate	Flammability..... 0
Reactivity.....	1	Slight	1	Slight	Reactivity..... 1
Personal Protection.....	X	Minimal	0	Insignificant	Special Precautions..... None