

GASKET MAKER

Hi-Temp Red Silicone

Form: Aerosol (Solid Paste)

Color: Red

Odor: Acetic Acid

pH: N/D

Solubility (in water): No data available
(in mineral spirits): No data available

VOC Content (% by wt): N/D

Flash Point (Closed Cup): >212°F

Specific Gravity: 1.007 g/cm³

Density: 8.40 lbs/gal

Storage Stability (at 70°F): 1 year

Ingredients

C.A.S. #

Triacetoxyethylsilane 17689-77-9
Methylsilanetriyl triacetate..... 4253-34-3
1,1-Difluoroethane, liquefied,
under pressure 75-37-6

Forms In-place Gaskets For:

- **Oil & Transmission Pans**
- **Oil & Water Pumps**
- **Valve & Timing Chain Covers**
- **Electric Motors**
- **Electrical Control Boxes**
- **Gear Boxes**
- **Compressors**
- **Machine Covers**

DIRECTIONS: Surface must be clean, dry and free of oil, tar, dirt and dust for best adhesion. Hold can at 45° angle and apply a continuous bead of 1/16” to 1/8” to the mating surface, encircling all bolt holes. For adhesion to both parts assemble immediately. For one part adhesion, allow 10 to 15 minutes for bead to skin. Assemble parts but do not squeeze gasket out by over tightening bolts. Starts to cure immediately, fully cures in 24 hours and reaches optimum strength in 7 days.

Note: Not recommended for use on cylinder heads, exhaust manifolds, intake manifolds, carburetors, or continuous immersion in gasoline.

HMIS®			NFPA®		
Health	1	Severe 4	Extreme	Health.....	1
Flammability.....	2	Serious 3	High	Flammability.....	2
Reactivity.....	0	Moderate 2	Moderate	Reactivity.....	0
Personal Protection.....	X	Slight 1	Slight	Special Precautions.....	None
		Minimal 0	Insignificant		